

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 639 (1982): Gold Leaf [MTD 10: Precious Metals]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



IS : 639 - 1982

Indian Standard
SPECIFICATION FOR
GOLD LEAF
(*Second Revision*)

UDC 669.21.416



© Copyright 1982

INDIAN STANDARDS INSTITUTION
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

Price Rs 5.00

Gr. 2

April 1982

Indian Standard

SPECIFICATION FOR GOLD LEAF

(Second Revision)

Precious Metals Sectional Committee, SMDC 13

Chairman

SHRI A. W. CHAWATHE

Representing

India Government Mint (Ministry of Finance),
Bombay

Members

SHRI R. S. AMBEKAR	Bharat Bullion Refinery, Ahmadabad
SHRI J. J. SHRIKANDE (Alternate)	
SHRI D. G. K. BALIGA	Bharat Gold Mines Pvt Ltd, Oorgaum
SHRI J. NAGESH BHATT	Indian Telephone Industries Ltd, Bangalore
SHRI A. DWARKANATH (Alternate)	
SHRI SHASHIKANT S. CHOKSI	Ravindra Hindustan Platinum Pvt Ltd, Bombay
SHRI CHANDRAKANT S. CHOKSI (Alternate)	
SHRI A. K. DAS	Ministry of Defence (DGI), New Delhi
SHRI P. K. SEN (Alternate)	
SHRI H. P. DUBEY	National Test House, Calcutta
SHRI P. GOPALKRISHNAYYA	Tamil Nadu Jewellers' Federation, Madras
SHRI J. N. KANSARA	Gujarat Bullion Refinery, Ahmadabad
SHRI B. S. KANSARA (Alternate)	
SHRI DHARAMVEER KAPOOR	All India Sarafa Association, Delhi
SHRI PREM NATH KHANNA (Alternate)	
DR C. S. P. IYER	Bhabha Atomic Research Centre, Bombay
DR T. P. RADHAKRISHNAN (Alternate)	
SHRI S. C. MOHANTI	Hutti Gold Mines Co Ltd, Hutti (Karnataka)
SHRI J. S. GURARAJ NAIK (Alternate)	
SHRIMATI PUSHPA MOTWANI	Consumer Guidance Society of India, Bombay
SHRIMATI SHARDA JOSHI (Alternate)	
SHRI R. C. PALHAN	Export Inspection Council of India, New Delhi
SHRI J. P. MAIKHURI (Alternate)	
SHRI K. RAJAGOPALAN	Regional Office of the Gold Control Administrator (Ministry of Finance), Bombay
SHRI M. P. REGE (Alternate)	

(Continued on page 2)

© Copyright 1982

INDIAN STANDARDS INSTITUTION

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

(Continued from page 1)

Members

SHRI K. S. RANGARAJAN

SHRI M. K. BANERJEE (Alternate)

SHRI BHARAT SAHAY

SHRIMATI S. PARAKASH (Alternate)

SHRI C. K. SHAH

SHRI S. P. SONAWALLA (Alternate)

SHRI AMRITLAL G. SONAWALLA

SHRI SHANTILAL NARANDAS (Alternate)

DR V. SUBRAMANIAN

SHRI NATWAR T. ZAVERI

SHRI NIRMAL KUMAR RAKYAN (Alternate)

SHRI C. R. RAMA RAO,

Director (Struc & Met)

Representing

Directorate General of Technical Development,
New Delhi

All India Handicrafts Board, New Delhi

National Refinery Pvt Ltd, Bombay

Bombay Bullion Association Ltd, Bombay

Government Dental College and Hospital, Bombay

The Gem & Jewellery Export Promotion Council,
Bombay

Director General, ISI (*Ex-officio Member*)

Secretary

SHRI O. N. DAS GUPTA
Deputy Director (Met), ISI

Indian Standard
SPECIFICATION FOR
GOLD LEAF
(*Second Revision*)

0. F O R E W O R D

0.1 This Indian Standard (Second Revision) was adopted by the Indian Standards Institution on 29 January 1982, after the draft finalized by the Precious Metals Sectional Committee had been approved by the Structural and Metals Division Council.

0.2 This standard was first published in 1955 and subsequently revised in 1965. This standard covers the material used for edible purposes, as in AYURVEDIC and UNANI systems of medicine and as a coating on sweets, PAN and other eatables. This standard also covers gold leaf used for other commercial purposes besides paint industry, such as its use in temples and in leather industry. Accordingly, two grades have been specified in this specification. Grade 1 is intended to cover its use for edible purposes and Grade 2 for commercial purposes. Very high purity gold has been recommended for edible purposes in order to avoid possibilities of contamination due to harmful elements. Since gold leaf may be used for edible purposes, the maximum permissible impurity limits of harmful elements specially for arsenic, lead, cadmium and mercury have been specified in this revision.

0.3 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS : 2-1960*. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

1. SCOPE

1.1 This specification covers the requirements of two grades of gold leaf used for edible and commercial purposes.

*Rules for rounding off numerical values (revised).

2. PURITY

2.1 The gold content of gold leaves shall be of minimum fineness as specified below:

	<i>Fineness</i>
Grade 1 (For medicinal and edible purposes)	999/1 000 fine The maximum permissible impurities for Grade 1 are as follows: Lead 2.5 ppm Arsenic 1.1 ppm Cadmium 0.8 ppm Mercury 0.01 ppm
Grade 2 (For commercial purposes)	970/1 000 fine (23.3 carat)

2.1.1 The gold content shall be determined either by the method specified in IS : 1418-1972* or any other established instrumental/chemical method. In case of dispute the procedure in the latest edition of IS : 1418-1972* for chemical analysis shall be the referee method.

2.1.2 The Indian Standard for determination of lead, arsenic, cadmium and mercury is under preparation. Until this standard is published, the method for determination of these elements shall be as agreed to between the purchaser and supplier.

3. SUPPLY OF MATERIAL

3.1 General requirements relating to the supply of material shall conform to IS : 1387-1967†.

4. REQUIREMENTS

4.1 **Workmanship** — Gold leaf shall be in the form of sheet free from creases and folds.

4.2 Weight

4.2.1 *For Grade 1* — Each pack (see 5.3) shall weigh 15 g.

*Method for assaying of gold in gold and gold alloys (*first revision*).

†General requirements for the supply of metallurgical materials (*first revision*).

4.2.2 For Grade 2 — Each pack (*see* 5.3) shall weigh either 10 g or 8 g depending on the size [*see* 4.3 (b)].

4.2.3 Tolerance — Tolerance on weights specified in 4.2.1 and 4.2.2 shall be ± 0.15 g.

4.3 Shape and Size — Unless otherwise specified, the gold leaf of Grade 1 and Grade 2 may be supplied in assortments of approximate shape and size as given below:

- a) Nearly round shape for Grade 1, and
- b) 150×175 mm (for 10 g weight) and 125×150 mm (for 8 g weight) for Grade 2.

5. PACKING

5.1 Books shall be properly packed in a suitable container so as to prevent damage due to creasing or bending in transit.

5.2 Gold leaf shall be supplied in either of the following two forms as specified by the purchaser:

- a) *Detachable (for Grade 1)* — In books with gold leaf loosely placed in between white tissue paper; or
- b) *Non-detachable (for Grade 2)* — In books with the gold leaf pressed on white tissue paper to prevent gold leaf becoming detached from paper due to draughts or air-currents.

5.3 A pack shall contain 100 leaves in 10 books each having 10 leaves.

6. SAMPLING AND CRITERIA FOR CONFORMITY

6.1 Lot — In any consignment, minimum of ten packs shall constitute a lot.

6.2 The number of packs to be sampled from each lot for the purposes of workmanship, dimensional and weight requirements and also for assay shall be as given in Table 1. These packs shall be selected at random preferably with the help of random number tables (*see* IS : 4905-1968*).

6.3 All the packs selected as per col 2 of Table 1 shall be examined for workmanship, dimensional and weight requirements. There shall be no failure if the lot is to be accepted for these requirements.

*Methods for random sampling. (Reaffirmed 1978).

TABLE 1 SCALE OF SAMPLING

(Clauses 6.2 and 6.3)

NO. OF PACKS IN THE LOT	SAMPLE SIZE FOR WORKMANSHIP, DIMENSIONAL AND WEIGHT REQUIRE- MENTS	NO. OF DETERMI- NATIONS FOR ASSAY
(1)	(2)	(3)
10 to 25	8	3
26 „ 50	13	4
51 and above	20	5

6.4 The number of determinations to be carried out for assay shall be as given in col 3 of Table 1. For this purpose at least 2 packs shall be drawn for each determination and 2 leaves from each pack shall be taken out. A composite sample of 500 mg (for Grade 1) and 250 mg (for Grade 2) shall be prepared out of the 4 gold leaves taken above. This process is to be repeated for each determination of assay. There shall be no failure in respect of assay if the lot is to be accepted for this characteristic.

7. MARKING

7.1 Each pack shall be marked with the following information:

- a) *The grade,
- b) The fineness of gold leaves,
- c) Net weight of one pack,
- d) Weight of the tissue papers,
- e) Actual weight of gold leaves,
- f) The approximate shape and size of the gold leaf, and
- g) Trade mark or name of the manufacturer.

7.1.1 The material may also be marked with the ISI Certification Mark.

NOTE— The use of the ISI Certification Mark is governed by the provisions of the Indian Standards Institution (Certification Marks) Act, and the Rules and Regulations made thereunder. The ISI Mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard under a well-defined system of inspection, testing and quality control which is devised and supervised by ISI and operated by the producer. ISI marked products are also continuously checked by ISI for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of the ISI Certification Mark may be granted to manufacturers or processors, may be obtained from the Indian Standards Institution.

*In case of Grade 2 gold leaf, the marking shall include the words 'not to be used for edible purposes'.

INTERNATIONAL SYSTEM OF UNITS (SI UNITS)

Base Units

QUANTITY	UNIT	SYMBOL
Length	metre	m
Mass	kilogram	kg
Time	second	s
Electric current	ampere	A
Thermodynamic temperature	kelvin	K
Luminous intensity	candela	cd
Amount of substance	mole	mol

Supplementary Units

QUANTITY	UNIT	SYMBOL
Plane angle	radian	rad
Solid angle	steradian	sr

Derived Units

QUANTITY	UNIT	SYMBOL	DEFINITION
Force	newton	N	$1 \text{ N} = 1 \text{ kg.m/s}^2$
Energy	joule	J	$1 \text{ J} = 1 \text{ N.m}$
Power	watt	W	$1 \text{ W} = 1 \text{ J/s}$
Flux	weber	Wb	$1 \text{ Wb} = 1 \text{ V.s}$
Flux density	tesla	T	$1 \text{ T} = 1 \text{ Wb/m}^2$
Frequency	hertz	Hz	$1 \text{ Hz} = 1 \text{ c/s (s}^{-1}\text{)}$
Electric conductance	siemens	S	$1 \text{ S} = 1 \text{ A/V}$
Electromotive force	volt	V	$1 \text{ V} = 1 \text{ W/A}$
Pressure, stress	pascal	Pa	$1 \text{ Pa} = 1 \text{ N/m}^2$

INDIAN STANDARDS INSTITUTION

Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002

Telephones : 26 60 21, 27 01 31

Telegrams : Manaksanstha

Regional Offices:

		Telephone
Western : Novelty Chambers, Grant Road	BOMBAY 400007	37 97 29
Eastern : 5 Chowringhee Approach	CALCUTTA 700072	27 50 90
Southern : C.I.T. Campus	MADRAS 600113	41 24 42
Northern : B69, Phase VII	S.A.S. NAGAR (MOHALI) 160051	—

Branch Offices:

'Pushpak', Nur Mohamed Shaikh Marg, Khanpur	AHMADABAD 380001	2 03 91
'F' Block, Unity Bldg, Narasimharaja Square	BANGALORE 560002	22 48 05
Gangotri Complex, Bhadbhada Road, T.T. Nagar	BHOPAL 462003	6 27 16
22E Kalpana Area	BHUBANESHWAR 751014	5 36 27
5-8-56 C. N. Gupta Marg	HYDERABAD 500001	22 10 83
R 14 Yudhister Marg, C Scheme	JAIPUR 302005	6 98 32
117/418 B Sarvodaya Nagar	KANPUR 208005	4 72 92
Patliputra Industrial Estate	PATNA 800013	6 28 08
Hantex Bldg (2nd Floor), Rly Station Road	TRIVANDRUM 695001	32 27